

Customized Versus Standard Implant Abutments: A Comprehensive Narrative Review of Biomechanical Performance, Peri-implant Tissue Response, Esthetic Outcomes, and Digital Workflow Integration

Jesus J Colmenares P¹, Noris M. Gil², Cristian Villamizar³

¹Universidad de Carabobo, Venezuela. Universidad de Guanajuato. Master in Orthodontics and Facial Orthopedics, Mexico.

²Universidad de Carabobo, Venezuela. ORCID 0009-0004-6819-3141

³Santo Tomas University, Bucaramanga, Colombia. ORCID: 0009-0003-6954-9413

Abstract

Implant abutments serve as the critical biomechanical and biological interface between the osseointegrated fixture and the prosthetic crown. As digital dentistry has expanded access to computer-aided design and computer-aided manufacturing (CAD/CAM) technology, individualized customized abutments have become an increasingly viable alternative to conventional prefabricated stock components. This narrative review examines the comparative performance of customized and standard abutments across four domains: biomechanical behavior, peri-implant tissue response, esthetic outcomes, and digital workflow integration. Current evidence suggests that customized abutments offer meaningful advantages in emergence profile management, soft tissue conditioning, peri-implant mucosal stability, and anterior esthetic outcomes. Biomechanical performance appears comparable between both types when appropriate materials and connection geometries are selected. Long-term randomized clinical trials using standardized outcome criteria remain scarce; therefore, definitive superiority cannot yet be established. Future research should incorporate standardized reporting frameworks to improve comparability across studies.

Key words: Dental implants; Implant abutments; Computer-aided design; CAD-CAM; Peri-implant tissues; Esthetics, Dental; Biomechanics; Digital dentistry.

INTRODUCTION

Dental implants have become a cornerstone of modern restorative dentistry, offering a reliable and well-documented solution for the rehabilitation of partial and complete edentulism. The long-term success of an implant-supported restoration depends not only on osseointegration of the fixture but also on the performance of the prosthetic components that connect the implant to the definitive crown. Among these, the implant abutment occupies a central role, functioning simultaneously as the biomechanical load-transfer element and as the biological scaffold around which peri-implant soft tissue architecture is organized. Despite this importance, abutment selection has historically received less attention than implant design or surgical technique. [1,2]

Abutment design evolved from simple prefabricated titanium components offered in a limited range of heights

and diameters toward stock, semi-adjustable, and fully individualized options. The introduction of CAD/CAM technology represented a genuine turning point, allowing clinicians and laboratory technicians to design and manufacture abutments that closely match each patient's implant position, gingival architecture, and esthetic requirements. [3,4]

The clinical limitations of standard prefabricated abutments are well recognized in esthetic or anatomically challenging cases.

Corresponding Author: Jesus J Colmenares P, Universidad de Carabobo, Venezuela. Universidad de Guanajuato. Master in Orthodontics and Facial Orthopedics, Mexico.

Because stock abutments are manufactured to fit an average patient, their fixed emergence angles, standardized heights, and circular cross-sections frequently fail to accommodate non-ideal implant positioning, complex gingival contours, or the esthetic demands of the anterior zone. When these limitations are encountered, clinicians face the choice of extensive manual modification, accepting a compromised result, or investing in a customized solution. [3,5]

Implant-supported restorations are now among the most frequently provided options for tooth replacement, and long-term data show high durability: a systematic review and sensitivity meta-analysis estimated ten-year implant survival at approximately 96 percent. [6] These figures, however, do not capture the burden of

prosthetic complications, peri-implant disease, or patient dissatisfaction associated with suboptimal component choices. [1] Even incremental improvements in abutment design and selection, therefore, carry a substantial collective clinical impact.

This narrative review provides a structured comparison of customized and standard implant abutments across four clinically relevant domains: (1) biomechanical performance; (2) peri-implant tissue response; (3) esthetic outcomes in the anterior zone; and (4) digital workflow integration. The FDI World Dental Federation criteria are used as a unifying outcome framework throughout. [7,8]

Table 1. Comparative Overview of Standard Versus Customized Implant Abutments Across Four Clinical Domains [5,6,7]

Domain	Standard Abutments	Customized Abutments
Biomechanics	Predictable load distribution under ideal angulation; limited correction for off-axis loading; screw loosening rate ~23.9% (EH) to 16.0% (conical)	Individualized angulation correction, optimized occlusal force redirection; hybrid Ti-base designs improve fracture resistance; similar long-term survival when properly designed
Peri-implant biology	Round profile requires secondary tissue shaping; higher soft tissue compression at crown insertion; microgap varies by connection type	Anatomical emergence conditioning from early healing; reduced mucosal compression; more favorable papilla indices and pink esthetic scores in controlled studies
Esthetic outcomes	Fixed profile limits anterior esthetic control; titanium gray show-through in thin biotypes; limited subgingival contouring	Individualized emergence profile; papilla preservation; zirconia or hybrid options reduce metallic show-through; better PES and patient-reported satisfaction
Digital workflows	Compatible with conventional impressions; limited design flexibility; lower initial cost	Requires digital impression and CAD design; higher upfront laboratory investment; reduced long-term complication burden; chairside or lab-based fabrication options available

BIOMECHANICAL PERFORMANCE

The biomechanical performance of implant-supported restorations depends on the interaction between component geometry, material properties, and the functional loading environment. The primary design objective is to facilitate stable load transfer to the surrounding bone while preserving the integrity of the implant-abutment joint over time. [9,10]

Stress Distribution and Finite Element Analysis Evidence

Finite element analysis has provided quantitative insight into how design variables affect stress transfer at the implant-bone interface. The type of implant-abutment connection exerts a particularly strong influence on stress distribution, and internal tissue-level connections have generally demonstrated more favorable biomechanical

behavior than internal bone-level configurations, with peak concentrations occurring at the connection margin. [9] Implant diameter is another determinant of cortical bone stress, with wider-diameter implants showing lower stress concentrations than regular-diameter fixtures. [9] With respect to macro-geometry, axially loaded parallel-walled implants exhibit lower peri-implant bone strain than tapered designs but are more sensitive to oblique loading, while conical and Morse taper designs distribute forces along their inner walls more evenly. [10,11]

Standard Abutments: Strengths and Limitations

Prefabricated titanium abutments provide reliable and predictable biomechanical performance when implants are placed in ideal three-dimensional positions with favorable angulation, making them an appropriate and cost-effective choice in straightforward posterior




Figure 1. Clinical decision algorithm for abutment selection across esthetic zone status, tissue biotype, implant angulation, material choice, and connection design. Teal = customized pathway; gray = standard pathway; purple = connection design recommendation. Based on references [1, 2, 3, 13, 14]

cases. [3] However, because standard abutments cannot compensate for off-axis implant placement, unfavorable lateral and oblique forces cannot be redirected into more axially aligned vectors, increasing stress concentration at the crestal bone. [3] In addition, the inherently circular cross-section of most prefabricated abutments requires secondary tissue shaping at the time of definitive crown placement, a process associated with patient discomfort and a risk of soft tissue recession. [12]

Customized Abutments: Angulation Correction and Emergence Profile Alignment

Customized abutments fabricated via CAD/CAM workflows address the principal limitations of prefabricated components by providing individualized solutions tailored to each patient's anatomy. [5] Beyond correcting prosthetic alignment relative to the loading axis, customized abutments allow precise management of the subgingival emergence profile: rather than relying on the definitive crown to compress and reshape peri-implant tissue, customized healing abutments or anatomical provisional restorations progressively condition the mucosa during healing. [12,13] Immediate provisionalization with

customized components reduces patient-reported pain at crown insertion and supports greater long-term mucosal stability than conventional round healing abutments, and in immediate placement facilitates closure of large extraction sockets that standard round components cannot adequately seal. [5,12]

Material Comparison

Titanium remains the reference material for implant abutments owing to its tensile strength, biocompatibility, and fatigue resistance under cyclic loading, and it is preferred in posterior locations and in patients with parafunctional habits. [14] Ytria-stabilized tetragonal zirconia abutments offer esthetic advantages, particularly in thin mucosal biotypes, but are more brittle than titanium; comparative analyses indicate that one-piece zirconia abutments are the most fracture-prone, whereas two-piece configurations behave more favorably. [14,15] Hybrid abutments that combine a prefabricated titanium base with a CAD/CAM ceramic superstructure offer a practical compromise between mechanical reliability and esthetics. [15]

Screw Loosening, Abutment Fracture, and Microgap

Screw loosening is among the most frequently reported technical complications in implant-supported single crowns, resulting from cyclic loss of preload. Connection design influences this outcome, with conical and Morse taper interfaces generally retaining preload better and providing a tighter microbial seal than flat-to-flat external hexagonal designs. [16] Abutment fracture, while less common, can be irreversible, and ceramic abutments are particularly vulnerable at the internal connection. [15] The implant-abutment microgap is an inherent feature of two-piece systems; gaps are considered clinically relevant once they exceed roughly ten micrometers because of

the associated risk of bacterial colonization, and original components tend to exhibit smaller microgaps than non-original compatible alternatives, generally within clinically acceptable thresholds. [17]

Consequences of Mechanical Failure

Joint instability or large microgaps create conditions for bacterial infiltration, triggering pro-inflammatory cytokine release and driving soft tissue inflammation and progressive peri-implantitis. [18] Component fractures may require complex retrieval procedures, and when remnants cannot be removed from an internal connection, explantation of the entire fixture may become necessary, with substantial additional treatment time, cost, and patient burden. [15]




Figure 2. Left panel: mean torque loss (%) by implant-abutment connection type; lower values indicate better screw retention [12,15]. Right panel: mean implant-abutment connection microgap (μm) by abutment origin; all values fall within the 10 μm clinical threshold [16].

PERI-IMPLANT TISSUE RESPONSE AND MARGINAL BONE STABILITY

The Implant-Abutment Interface as a Microbial Reservoir

In two-piece systems, a microscopic gap at the implant-abutment connection is an inherent limitation. Once colonized, this microgap serves as a persistent reservoir, and cyclic loading-induced flexion promotes the release of bacterial products into the peri-implant environment, a recognized driver of peri-implant mucositis and, over time, peri-implantitis. Connection design influences the magnitude of this problem, with conical connections offering better resistance to microbial colonization than external hexagonal designs, although no currently available system achieves a fully hermetic seal, and the literature

remains heterogeneous in design and microbiological criteria. [18]

Marginal Bone Loss: Standard Versus Customized Abutments

A five-year follow-up comparing CAD/CAM customized abutments with prefabricated alternatives reported similar trends in marginal bone level changes over time, suggesting that both approaches can maintain peri-implant bone stability under appropriate protocols. [19] Research evaluating customized healing abutments in immediate placement indicates they are as effective as conventional healing abutments in maintaining bone crest height and keratinized mucosa thickness, while a systematic review found more favorable peri-implant and esthetic outcomes for customized compared with conventional healing abutments. [12,20]

Emergence Profile Angle and the Biological Width

The angulation and overhang of the subgingival emergence profile have direct consequences for peri-implant tissue health. A convex emergence profile compresses the mucosa and has been associated with a higher frequency of recession, whereas a concave profile provides space for soft tissue maturation; randomized evidence supports

concave profiles, particularly in the anterior region, where mid-facial recession poses an esthetic risk. [21] Subcrestal placement with Morse taper connections at depths of one to two millimeters below the alveolar crest has been associated with lower peak cortical bone stress than equicrestal or supracrestal positioning. [22]




Figure 3. Subgingival emergence profile anatomy showing the three clinically relevant zones for customized abutment design. Zone C (crestal, teal): convex profile sealing the microbial interface at the implant platform. Zone B (bounded, amber): mandatory concave contour providing space for augmented soft tissue maturation without mechanical pressure. Zone E (esthetic, purple): non-circular crown emergence contour supporting papilla fill and zenith replication. Based on Endres et al. [18] and Ruhstorfer et al. [13].

Platform Switching and Customized Abutment Design

The platform-switching concept, in which a prosthetic component of smaller diameter than the implant platform is used, shifts the stress concentration zone away from the crestal bone and has been associated with reduced marginal bone loss in a systematic review and meta-analysis. [23] Customized abutments can incorporate platform-switching geometry while simultaneously individualizing the emergence profile and transmucosal contour, potentially combining biological and esthetic benefits. [3,23]

Surface Characteristics and Soft Tissue Integration

The surface properties of the transmucosal portion influence how effectively the peri-implant mucosa seals around the component. Titanium remains the benchmark for biocompatibility and corrosion resistance, although metallic abutments in thin biotypes are associated with mucosal discoloration. Zirconia offers superior esthetics in thin tissues and favorable soft tissue responses owing to its chemical inertness, while polyetheretherketone (PEEK) has attracted interest because its modulus of elasticity is closer to cortical bone than titanium or zirconia; its bio-

inert nature, however, limits direct integration and current evidence does not support routine use as a definitive abutment material. [14]

ESTHETIC OUTCOMES AND SOFT TISSUE ARCHITECTURE

Why Standard Abutments Fall Short in the Anterior Zone

The anterior esthetic zone demands soft tissue control and color integration that standard prefabricated abutments are inherently limited in providing, because their circular profiles cannot replicate the natural, non-circular emergence anatomy of anterior teeth and leave the final restoration to shape the gingival margin. [12] From a materials perspective, metallic titanium abutments present an esthetic liability in thin tissues, where the gray substrate becomes visible through the mucosa; in vitro spectrophotometric work has shown that titanium produces color changes exceeding the perceptible threshold in thin mucosa, whereas zirconia produces changes close to or below that threshold. [25]

Customized Abutments and Emergence Profile Engineering

Customized abutments allow clinicians to design the transmucosal profile from the outset, shaping the peri-implant mucosa to mimic a natural tooth. Customized healing abutments placed at surgery or uncovering create an anatomical soft tissue tunnel that the definitive restoration can follow without aggressive compression, and the conditioned profile is subsequently transferred to the definitive abutment through a customized impression or digital copy workflow. [12,13] Comparative data report more favorable peri-implant and esthetic outcomes when customized components are used. [20]

Abutment Color and Transmucosal Esthetics

The abutment material influences the appearance of both the peri-implant mucosa and the final restoration. A systematic review and meta-analysis of spectrophotometric studies found that abutment material affects peri-implant soft tissue color, with titanium producing greater discoloration than tooth-colored materials, particularly in thin mucosa. [26] At the crown level, a metallic background can compromise the final ceramic shade; increasing ceramic thickness and applying a thin opaque porcelain layer have been shown to improve masking of the metallic substrate. [27]

PES and WES as Outcome Measures

The Pink Esthetic Score (PES) and White Esthetic Score (WES) provide standardized tools for evaluating soft- and

hard-tissue esthetic outcomes around implant restorations. The PES evaluates parameters such as mucosal level, contour, color, texture, and papilla fill, while the WES focuses on crown form, surface texture, translucency, and color match. [28,29] Total esthetic scores are influenced by multiple interacting factors beyond abutment type, including tissue volume, biotype, and the quality of the surgical and provisional phases. [21]

Immediate Provisionalization and Tissue Conditioning

Immediate provisionalization with screw-retained customized temporaries allows tissue conditioning to begin at an early stage, guiding the healing mucosa into a natural anatomical scallop; the submucosal contour is progressively refined through the crestal, bounded, and esthetic subgingival zones, and the matured profile is then transferred to the definitive restoration, which lowers patient-reported pain at crown insertion compared with conventional protocols. [12,13]

DIGITAL WORKFLOW INTEGRATION AND CAD/CAM CUSTOMIZATION

Digital Implant Workflow Overview

Digital workflows have become an established component of contemporary implant prosthodontics, enabling a transition from conventional impressions toward a fully digital restorative pathway. The process typically begins with intraoral scanning and acquisition of implant position through scan bodies, followed by CAD of the abutment and restoration, transfer to CAM systems, and clinical delivery. The accuracy of the chain depends on precise transfer of implant position, making digital impression accuracy a critical determinant of customized-abutment fit. [4,13]

Intraoral Scanners and Scan Body Accuracy

Scan bodies serve as reference markers that transfer the three-dimensional implant position into the virtual environment. A systematic review reported that scan body characteristics such as height, diameter, geometry, material, and retention design influence the trueness and precision of digital implant scans, that contemporary scanners generally achieve clinically acceptable accuracy for single implants and short spans, and that no universally superior scan body design has been identified. [30]

CAD Software for Abutment Design

CAD software allows control over emergence profile geometry, correction of angulation discrepancies, and customization of margin depth according to peri-implant tissue characteristics, and it permits the abutment shoulder to be positioned precisely relative to the mucosal

margin. This is clinically relevant because residual excess cement at the abutment margin is a recognized risk factor for peri-implant disease; one prospective endoscopic study associated excess cement with peri-implant disease in the majority of affected sites. [24]

Milling Versus Additive Manufacturing

Subtractive CAD/CAM milling remains the most established method for fabricating definitive abutments, with high dimensional accuracy and an extensive evidence base, and surface quality in the transmucosal region is relevant because roughness influences bacterial colonization and tissue response. [31] Additive manufacturing offers advantages in material efficiency and geometric complexity, but comparative laboratory work has shown lower fracture resistance for additively manufactured than for milled restorations, supporting milling as the current reference standard while additive manufacturing is most appropriate in the provisional phase. [32]

Ti-Base Hybrid Abutments

Ti-base hybrid abutments combine the mechanical reliability of a titanium implant connection with the esthetic advantages of CAD/CAM ceramic superstructures, and their long-term success depends substantially on the integrity of the adhesive interface between the titanium base and the ceramic component. [33] Under FDI criteria, loss of retention, partial debonding, and fracture of the restorative complex are classified within the functional domain and should be systematically documented. [7,8]

Cost and Workflow Considerations

Customized CAD/CAM abutments incur higher initial laboratory and manufacturing costs than conventional stock options. Their potential to reduce biological complications and prosthetic remakes may offset some of this upfront investment over time, and five-year data indicate stable peri-implant conditions for CAD/CAM-customized abutments; however, direct cost-effectiveness comparisons remain scarce. [19] Digital customization can be accomplished chairside or through laboratory-based workflows, and the choice should be guided by case complexity, available technology, operator expertise, and economic considerations. [33]

Emerging Materials: PEEK Abutments

PEEK has emerged as a promising biomaterial owing to favorable esthetics, a low elastic modulus, radiolucency, and biocompatibility. Current evidence does not support PEEK as a definitive replacement for titanium in most scenarios, and a systematic review concluded that its most appropriate current application is as a provisional

abutment material, with additional long-term clinical studies required before routine definitive use can be recommended. [34]

Standardized Outcome Assessment

To improve comparability among studies evaluating customized and standard abutments, outcomes should be interpreted using standardized criteria. The FDI World Dental Federation criteria classify restorative outcomes into esthetic, functional, and biological domains, and their adoption would improve consistency in reporting and facilitate meaningful comparison across studies evaluating different abutment designs. [7,8]

CONCLUSIONS

Customized implant abutments offer clear advantages when individualized soft-tissue management, precise emergence-profile control, and anterior esthetic integration are central to treatment success, and they simplify the clinical protocol for immediate placement. Biomechanical performance does not appear to differ categorically between customized and standard abutments when appropriate materials and connection geometries are selected, and five-year data indicate comparable marginal bone stability between the two approaches. Stock abutments remain a predictable, cost-effective solution in posterior regions with favorable implant positioning and limited esthetic demands, and the decision to invest in a customized solution should be driven by clinical necessity.

The most significant limitation of the current evidence base is the scarcity of long-term randomized clinical trials that simultaneously compare customized and standard abutments across esthetic, biological, functional, and economic outcomes using standardized criteria. Adoption of the FDI World Dental Federation criteria as a shared outcome framework would substantially improve the comparability of future studies.

REFERENCES

1. Sailer I, Karasan D, Todorovic A, Ligoutsikou M, Pjetursson BE. Prosthetic failures in dental implant therapy. *Periodontol* 2000. 2022;88(1):130-144.
2. James JR, Kharat A, Chinnakutti S, Kamble S, Mandal M, Das A. The future of dental implants: a narrative review of trends, technologies, and patient considerations. 2025.
3. Prpic V, Kosec P, Skec S, Catic A. Influence of design parameters on implant abutment performance: a scoping review. 2025.

4. Suganna M, Nayakar RP, Alshaya AA, Khalil RO, Alkhunaizi ST, Kayello KT, Alnassar LA. The digital era heralds a paradigm shift in dentistry: a cross-sectional study. *Cureus*. 2024;16(1):e53300.
5. Robaian A, Hamed MM, Ahmed Y, Hassanein FEA. Comparative evaluation of customized CAD/CAM vs. stock titanium abutments for immediate implant placement in class II extraction sockets: a randomized controlled trial. *Dent J (Basel)*. 2025;13(8):371.
6. Howe MS, Keys W, Richards D. Long-term (10-year) dental implant survival: a systematic review and sensitivity meta-analysis. *J Dent*. 2019;84:9-21.
7. Hickel R, Peschke A, Tyas M, Mjor I, Bayne S, Peters M, et al. FDI World Dental Federation clinical criteria for the evaluation of direct and indirect restorations. *J Adhes Dent*. 2010;12(4):259-272. =
8. Hickel R, Mesinger S, Opdam N, Loomans B, Frankenberger R, Cadenaro M, et al. Revised FDI criteria for evaluating direct and indirect dental restorations. *Clin Oral Investig*. 2023;27(6):2573-2592.
9. Lee H, Jo M, Sailer I, Noh G. Effects of implant diameter, implant-abutment connection type, and bone density on the biomechanical stability of implant components and bone: a finite element analysis study. *J Prosthet Dent*. 2022;128(4):716-728.
10. Pellizzer EP, Lemos CAA, Almeida DAF, de Souza Batista VE, Santiago Junior JF, Verri FR. Biomechanical analysis of different implant-abutment interfaces: an in silico analysis. *J Biomech*. 2020;109:109880.
11. Loehlein M, Motel C, Wichmann M, Matta RE. Influence of implant geometry on the surface strain behavior of peri-implant bone: a 3D analysis. *J Oral Implantol*. 2023..
12. Dutra MDZ, De Carli JP, Dallepiane FG, Facenda JC, Silva PRP, Dal Bello Y, Dogenski LC, Di Domenico MB, Corazza PH. Effectiveness of customized healing abutments in immediate implants: a randomized clinical trial. *Braz Oral Res*. 2025;39:e084.
13. De Moura AJ, Burgoa S, Rayes A, da Silva RLB, Ayres AP, Cortes ARG. Digital workflow for designing CAD/CAM custom abutments of immediate implants based on the natural emergence profile of the tooth to be extracted. *J Oral Implantol*. 2023;49(5):510-516.
14. Chen CC, Ding SJ, et al. Unveiling the characteristics and surface modification of titanium, zirconia, and polyetheretherketone dental implants. 2025.
15. Totou D, Naka O, Mehta SB, et al. Esthetic, mechanical, and biological outcomes of various implant abutments for single-tooth replacement in the anterior region: a systematic review. *Int J Implant Dent*. 2021;7(1):85.
16. Sammour SR, Xu Z, Ogawa T, Yoda N. Impact of implant abutment connection designs and cyclic loading on screw stability in dental implants: a systematic review and meta-analysis. *J Prosthodont Res*. 2023.
17. Sharifi R, Ghaffari T, Ghasemi S, Samadi Kafil H. Evaluation of microgap size and microbial microleakage at the implant fixture-abutment interface in original and compatible abutments. *J Prosthet Dent*. 2021.
18. Lauritano D, Moreo G, Lucchese A, Viganoni C, Limongelli L, Carinci F. The impact of implant-abutment connection on clinical outcomes and microbial colonization: a narrative review. *Materials (Basel)*. 2020;13(5):1131.
19. Chao KC, Salamanca E, Lin JCY, Linn TY, Renn TY, Sun YS, et al. Marginal bone level of dental implants using CAD/CAM customized abutment and prefabricated abutment: a five-year follow-up. *J Dent Sci*. 2025;20(2):1158-1167.
20. Ruhstorfer M, Guth JF, Stimmelmayer M, Waltenberger L, Schubert O, Graf T. Systematic review of peri-implant conditions and aesthetic outcomes of customized versus conventional healing abutments. *Int J Implant Dent*. 2024;10(1):61.
21. Endres J, Strauss FJ, Siegenthaler M, Naenni N, Jung RE, Thoma DS. Convex versus concave emergence profile of implant-supported crowns in the aesthetic zone: 3-year results of a randomized controlled trial. *J Clin Periodontol*. 2025;52(11):1605-1615.
22. Comuzzi L, Ceddia M, Di Pietro N, Inchingolo F, Inchingolo AM, Romasco T, et al. Crestal and subcrestal placement of Morse cone implant-abutment connection implants: an in vitro finite element analysis (FEA) study. *Biomedicines*. 2023;11(11):3077.
23. 23. Atieh MA, Ibrahim HM, Atieh AH. Platform switching for marginal bone preservation around dental implants: a systematic review and meta-analysis. *J Periodontol*. 2010;81(10):1350-1366.
24. Wilson TG Jr. The positive relationship between excess cement and peri-implant disease: a prospective clinical endoscopic study. *J Periodontol*. 2009;80(9):1388-1392.
25. Jung RE, Sailer I, Hammerle CHF, Attin T, Schmidlin P. In vitro color changes of soft tissues caused by restorative materials. *Int J Periodontics Restorative Dent*. 2007;27(3):251-257.

26. Pitta J, Zarauz C, Pjetursson B, Sailer I, Liu X, Pradies G. A systematic review and meta-analysis of the influence of abutment material on peri-implant soft tissue color measured using spectrophotometry. *Int J Prosthodont*. 2020;33(1):39-47.
27. Sun X, Li L, Zhang H, Feng H, Liu X, Qiu Y, et al. Effect of opaque porcelain on color and aesthetic outcomes of titanium-abutment implant restorations. *J Prosthet Dent*. 2022. [volume/pages to confirm]
28. Furhauser R, Florescu D, Benesch T, Haas R, Mailath G, Watzek G. Evaluation of soft tissue around single-tooth implant crowns: the pink esthetic score. *Clin Oral Implants Res*. 2005;16(6):639-644.
29. Belser UC, Grutter L, Vailati F, Bornstein MM, Weber HP, Buser D. Outcome evaluation of early placed maxillary anterior single-tooth implants using objective esthetic criteria: a cross-sectional, retrospective study in 45 patients with a 2- to 4-year follow-up using pink and white esthetic scores. *J Periodontol*. 2009;80(1):140-151.
30. Gomez-Polo M, Donmez MB, Cakmak G, Yilmaz B, Revilla-Leon M. Influence of implant scan body design on intraoral scanning accuracy: a systematic review. *J Prosthodont*. 2023;32(Suppl 2):165-180.
31. Tarte DA, Manolea HO, Ionescu M, Ginku O, Amarascu MO, Popescu AM, et al. A microscopy evaluation of emergence profile surfaces of dental custom CAD/CAM implant abutments and stock abutments. *J Pers Med*. 2024;14(7):699.
32. Fracture resistance of additive manufactured and milled implant-supported interim crowns. *J Prosthet Dent*. 2021. [authorship to confirm] *[nueva-verificada]*
33. Al-Thobity AM. Titanium base abutments in implant prosthodontics: a literature review. *Eur J Dent*. 2022;16(1):49-55.
34. Ghazal-Maghras R, Vilaplana-Vivo J, Camacho-Alonso F, Martinez-Beneyto Y. Properties of polyetheretherketone (PEEK) implant abutments: a systematic review. *J Clin Exp Dent*. 2022;14(4):e349-e358.

Cite this article: Jesus J Colmenares P, Noris M. Gil, Cristian Villamizar. *Customized Versus Standard Implant Abutments: A Comprehensive Narrative Review of Biomechanical Performance, Peri-implant Tissue Response, Esthetic Outcomes, and Digital Workflow Integration. International Journal of Research in Medical and Clinical Science (IJRMCS)*. 2026; 4(2): 09-17.

Copyright: © 2026. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.