

A Critical Review of the Mechanical Properties and Applications of Advanced High-Strength Steels in the Automotive Industry

¹Alabi Johnson Sunday, ²Obojobo Donatus Obukeajeta, ²Onyiriuka Frank, ⁴Moses Adondua Abah, ⁴Micheal Oladosu Abimbola

¹Department of Mechanical Engineering, Faculty of Engineering, Federal University Oye Ekiti, Ekiti State, Nigeria

²Department of Mechanical Engineering, Faculty of Engineering, Southern Delta University, Ozoro, Delta State, Nigeria

³Department of Mechanical Engineering, Faculty of Engineering, Delta State University, Abraka, Delta State, Nigeria

⁴ResearchHub Nexus Institute, Nigeria

Abstract

Advanced High-Strength Steels (AHSS) represent a new generation of steel grades that provide much higher strength and other advantageous properties than other materials while maintaining the high formability required for manufacturing. AHSSs help engineers meet requirements for safety, efficiency, emissions, manufacturability, durability, and quality at a low cost. The relevance of AHSSs is quickly increasing in the automotive industry, and AHSSs are the key material for vehicle mass reduction. Different types of AHSS help parts meet the varied performance demands in different areas of the vehicle, including both the crumple zone and passenger compartment. This review critically examines the mechanical properties, classifications which includes the first, second, and third generations, processing technologies, and automotive applications of AHSS. It discusses the evolution from conventional steels to AHSS, highlighting improvements in strength-ductility balance, crash energy absorption, and lightweighting potential. Key challenges such as formability limitations, springback, weldability, and cost are addressed alongside future prospects in third-generation AHSS and digital manufacturing integration. Findings indicate that AHSS continue to offer the best combination of performance, affordability, and sustainability for modern vehicle structures. The industrial relevance lies in their ability to simultaneously address stringent safety, fuel efficiency, and emission regulations while remaining cost-competitive with alternative lightweight materials.

Keywords: High-strength steels, Manufacture, Automotive industry, Technology, and Energy

INTRODUCTION

The automotive industry faces intense pressure to reduce vehicle weight for improved fuel efficiency and lower emissions while simultaneously enhancing passenger safety and maintaining affordability (Matlock, 2009). Global challenges such as stringent Corporate Average Fuel Economy (CAFE) standards, rising environmental concerns, and the transition toward electric vehicles have driven material innovation in vehicle manufacturing (De Moor, 2021). Conventional steels, which dominated automotive production for decades due to their low cost, good formability, and recyclability, became insufficient as they could no longer meet the conflicting demands of higher strength for safety and thinner gauges for weight reduction without compromising ductility and crash performance (Kuziak *et al.*, 2008). The evolution of steel materials in the automotive industry reflects continuous

efforts to balance strength, formability, and cost. Early mild steels offered excellent formability but limited strength. High-strength low-alloy (HSLA) steels provided incremental improvements, yet further weight reduction required a breakthrough (Hu *et al.*, 2021). This led to the emergence of Advanced High-Strength Steels (AHSS), which derive their properties from multi-phase complex microstructures. The response of the steel industry to new challenges is a rapid development of higher strength steels, named Advanced High Strength Steels (AHSS) (Kuziak *et al.*, 2008). AHSS are complex, sophisticated materials, with carefully selected chemical compositions and multiphase microstructures.

Corresponding Author: Moses Adondua Abah
ResearchHub Nexus Institute, Nigeria

The steel industry has responded to these needs and challenges by developing a variety of AHSS exhibiting varying strength and formability, alloy compositions (De Moor, 2021). AHSSs are a new generation of steel grades that provide much higher strength and other advantageous properties than other materials while maintaining the high formability required for manufacturing. Although steels are denser than Al alloys and Mg alloys, today's AHSSs have comparable specific rigidity (elastic modulus to density ratio) and specific strength (ultimate tensile strength [UTS] to density ratio) to those lightweight metals because of the much higher strength of AHSSs (Hu *et al.*, 2021).

The need for lightweight and fuel-efficient vehicles has become a primary driver. Studies show AHSS steel grades are growing faster in new automotive applications than alternative materials. Key reasons to deploy advanced high strength steels in automotive body structures include better performance in crash energy management and increased strength allowing this performance to be achieved with thinner materials, translating into lower vehicle weight (Matlock, 2009). The relationship between vehicle safety, weight reduction, and material selection is fundamental. Higher strength enables down gauging (thinner sheets) while maintaining or improving structural integrity during crashes. AHSS provide excellent energy absorption in deformation zones and high strength for intrusion resistance in passenger compartments. Three generations of AHSS have been developed. The first generation of AHSS includes DP, complex-phase, martensitic and low-carbon, and low-alloy TRIP steels. The second generation of AHSS includes the twinning-induced plasticity steels. Substantial

effort is currently being directed toward the development of third-generation AHSS (Hu *et al.*, 2021).

This review aims to explore current knowledge on the mechanical properties and automotive applications of AHSS. It examines the scientific principles behind their superior performance, classifications, processing routes, real-world applications, and remaining challenges. The scope focuses primarily on sheet steels used in body-in-white and structural components, drawing from peer-reviewed literature and industry technical reports published in indexed journals. By critically evaluating strengths and limitations, this review highlights why AHSS remain the material of choice for sustainable automotive manufacturing despite competition from aluminum, composites, and other alternatives. Conventional steels became insufficient because they could not simultaneously deliver the required combination of high strength for safety and sufficient ductility for complex forming operations demanded by modern vehicle designs.

CLASSIFICATION AND MICROSTRUCTURAL CHARACTERISTICS OF AHSS

Advanced High-Strength Steels (AHSS) are primarily steels with tensile strengths ≥ 500 MPa and complex microstructures of distinct phases, such as ferrite, martensite, bainite, austenite, and/or retained austenite in quantities sufficient to produce unique mechanical properties. AHSS are complex, sophisticated materials, with carefully selected chemical compositions and multiphase microstructures (Kuziak *et al.*, 2008). The principal difference between conventional HSLA steels




Fig1. Microstructures of different AHSS types

Source: Xia *et al.* (2025)

and AHSS is their microstructure. Conventional HSLA steels are single-phase ferritic steels with a potential for some pearlite. AHSS are primarily steels with a multiphase microstructure containing one or more phases other than ferrite, pearlite, or cementite (Kuziak *et al.*, 2008).

AHSS are classified into three generations based on their development timeline, alloying strategies, processing routes, and the resulting strength-ductility balance. First-generation AHSS achieve high strength through microstructural constituents like martensite and retained

austenite but often at the expense of formability (Hu *et al.*, 2021). Second-generation AHSS rely on high manganese content and twinning mechanisms for exceptional ductility. Third-generation AHSS aim to bridge the gap by combining high strength (>1000 MPa) with improved elongation (>20–30%) through novel processing such as quenching and partitioning or medium manganese alloying (Xia *et al.*, 2025).

As illustrated in Figure 1 above, the microstructure of

each AHSS type directly governs its mechanical behavior through phase interactions and deformation mechanisms. It compares; DP steel – ferrite + martensite islands; TRIP steel – ferrite + bainite + retained austenite; TWIP steel austenitic matrix with twinning; martensitic steel nearly full martensite.

As shown in Table 1, each generation and subtype offers distinct combinations of strength and ductility tailored to specific automotive performance requirements.

Table 1. Classification and characteristics of AHSS

AHSS Type	Microstructure	Tensile Strength (MPa)	D u c t i l i t y (Elongation %)	Typical Automotive Use
First-Generation (DP)	Ferrite + Martensite	500–1200	10–25	Crash structures, chassis parts
First-Generation (TRIP)	Ferrite + Bainite + Retained Austenite	600–1000	20–30	Energy-absorbing components
Second-Generation (TWIP)	Austenite (high Mn)	900–1200	50–70	High-formability structural parts
Third-Generation (Q&P)	Martensite + Retained Austenite	1000–1500	15–30	Lightweight safety-critical components
Third-Generation (Med-Mn)	Ultra-fine ferrite + Retained Austenite	900–1300	20–40	Next-generation body-in-white

Sources: Kuziak *et al.* (2008); De Moor, (2021); Hu *et al.* (2021); Xia *et al.* (2025)

First-Generation AHSS

The first generation of AHSS includes DP, complex-phase, martensitic and low-carbon, and low-alloy TRIP steels. Dual-phase (DP) steels consist of a ferritic matrix with islands of martensite. The martensite provides high strength while the ferrite ensures good ductility (De Moor, 2021). Transformation-induced plasticity (TRIP) steels contain retained austenite that transforms to martensite during deformation, enhancing work hardening and uniform elongation. Complex-phase (CP) steels feature fine grains of ferrite, bainite, and martensite for high strength and good hole expansion (Kuziak *et al.*, 2008; Hu *et al.*, 2021). These steels derive their properties from the composite effect of soft and hard phases, where structure property relationships are governed by phase fraction, size, and distribution. Higher martensite content increases strength but reduces formability.

Second-Generation AHSS

The second generation of Advanced High Strength Steels includes the twinning-induced plasticity steels (TWIP). TWIP steels are characterized by a fully austenitic microstructure with high manganese content (15–25 wt.%). The primary deformation mechanism is mechanical twinning, which dramatically increases work-hardening rate and results in exceptional strength-ductility combinations (De Moor, 2021; Xia *et al.*, 2025). Although offering superior formability, second-generation AHSS suffer from high alloying costs and challenges in weldability and galvanizing, limiting widespread adoption.

Third-Generation AHSS

The main target in developing the 3rd generation AHSS was to achieve the properties in between those of the 1st and 2nd generation AHSS at lower cost (De Moor, 2021). Third-generation AHSS, such as medium manganese steels and quenching and partitioning (Q&P) steels, rely on retained austenite in a bainite or martensite matrix. Q&P steels are produced by quenching to a temperature between Ms and

Mf followed by partitioning to stabilize retained austenite through carbon diffusion. Medium-Mn steels (3–12% Mn) achieve ultra-fine grain structures with high fractions of metastable austenite (Matlock, 2009; Perka *et al.*, 2022).

These steels improve the strength-ductility balance through transformation-induced plasticity and austenite stability control. Microstructural constituents such as retained austenite enable dynamic strain hardening, while martensite and bainite provide strength. The enhanced performance makes third-generation AHSS particularly suitable for complex automotive parts requiring both crash energy absorption and lightweighting (Kantanen *et al.*, 2022; Xia *et al.*, 2025).

MECHANICAL PROPERTIES OF ADVANCED HIGH-STRENGTH STEELS

Advanced High-Strength Steels (AHSS) exhibit a remarkable combination of mechanical properties that make them highly suitable for modern automotive applications. These properties include high tensile strength, yield strength, adequate ductility, superior fatigue resistance, good formability, and excellent crashworthiness. The multiphase microstructures of AHSS enable these balanced properties, allowing manufacturers to achieve significant weight reduction while enhancing vehicle safety and performance (Pereira *et al.*, 2024; Mohapatra *et al.*, 2026).

As illustrated in Figure 2, AHSS occupy a superior region in




Fig2. Strength–Ductility Relationship in AHSS: Graph showing tensile strength vs elongation with comparison among conventional steels, first-, second-, and third-generation AHSS

Sources: Huang *et al.*, (2022)

Table 2. Mechanical properties of common AHSS grades

Steel Grade	Yield Strength (MPa)	Tensile Strength (MPa)	Elongation (%)	Key Property
DP 590	330–430	590–700	20–26	Good formability and crash energy absorption
DP 980	550–700	980–1100	12–18	High strength for structural safety
TRIP 780	450–550	780–850	22–30	Enhanced work hardening and ductility
TWIP 980	500–600	980–1100	45–60	Superior formability
Q&P 980 (3rd Gen)	600–750	980–1200	20–28	Balanced strength-ductility
Medium-Mn (3rd Gen)	700–900	1100–1500	15–35	High strength with improved elongation

Sources: Schmitt *et al.* (2018); Huang *et al.* (2022)

the strength-ductility space, with third-generation grades providing improved combinations compared to earlier generations and conventional high-strength steels.

As shown in Table 2, AHSS grades provide a wide range of property combinations, enabling optimized material selection for different automotive components.

Strength–Ductility Relationship

The strength–ductility relationship in AHSS is a key advantage over conventional steels. While conventional steels typically show an inverse relationship where higher strength leads to lower ductility (Schmitt *et al.*, 2018), AHSS maintain better ductility through mechanisms such as transformation-induced plasticity (TRIP) and twinning-induced plasticity (TWIP). This balance allows for thinner

sheet gauges, contributing to vehicle lightweighting without sacrificing safety or manufacturability (Huang *et al.*, 2022; Schmitt *et al.*, 2018). Compared to aluminum alloys, AHSS generally offer higher absolute strength and better stiffness at lower cost, although aluminum may provide greater weight savings in specific non-structural parts.

Energy Absorption and Crash Performance

Crashworthiness is significantly enhanced in AHSS due to their high work-hardening capacity and ability to absorb impact energy (Jonsson, 2025). First- and third-generation AHSS excel in progressive deformation, protecting the passenger compartment while dissipating crash energy effectively. Studies on thin-walled structures demonstrate that AHSS outperform conventional steels




Fig3. Processing route for AHSS production

Source: Wróbel (2022)

in energy absorption under dynamic loading conditions (Mohapatra *et al.*, 2026). This property directly improves automotive safety by reducing intrusion and decelerating forces transmitted to occupants.

Fatigue and Wear Resistance

AHSS demonstrate superior fatigue resistance compared to conventional steels, primarily due to their high tensile strength and work-hardening behavior. The endurance limit increases with strength, and components benefit from bake-hardening effects during paint curing. This makes AHSS ideal for chassis, suspension, and structural parts subjected to cyclic loads (Pereira *et al.*, 2024).

Corrosion Resistance and Thermal Stability

Corrosion resistance in automotive AHSS is typically managed through advanced zinc-based coatings, which perform well even on high-strength grades. Thermal stability during manufacturing processes (such as hot stamping and paint baking) is excellent, with most grades

retaining their mechanical properties after exposure to elevated temperatures (Schmitt *et al.*, 2018; Kantanen *et al.*, 2022). In comparison with aluminum alloys, AHSS show competitive corrosion performance when properly coated and offer better joining compatibility in mixed-material designs.

Overall, the mechanical properties of AHSS provide a compelling solution to the automotive industry's demands for safer, lighter, and more fuel-efficient vehicles (Huang *et al.*, 2022). Their ability to outperform conventional steels while remaining cost-effective positions them as the primary material for body-in-white and structural applications. Ongoing development of third-generation AHSS continues to push the boundaries of the strength-ductility balance, further expanding their applications (Mohapatra *et al.*, 2026).

Manufacturing and Processing Techniques

Manufacturing and processing techniques for Advanced High-Strength Steels (AHSS) are critical in achieving the

desired multiphase microstructures and mechanical properties. Thermomechanical processing, hot stamping, cold rolling, annealing, and advanced welding technologies directly influence the final microstructure and performance

of AHSS components in automotive applications (Zhao *et al.*, 2018; Wróbel, 2022).

As illustrated in Figure 3, the typical processing route

Table 3. Key processing techniques for AHSS

Technique	Purpose	Effect on Microstructure	Industrial Advantages
Hot Stamping	Forming + Quenching	Fully martensitic	Complex shapes, ultra-high strength
Cold Rolling + Annealing	Thickness reduction & property control	Multi-phase (ferrite + martensite, etc.)	High productivity, cost-effective
Quenching & Partitioning	Retained austenite stabilization	Martensite + Retained Austenite	Improved ductility
Resistance Spot Welding	Assembly of components	Localized heat-affected zone	Fast, automated, widely used

Sources: Frohn-Sørensen *et al.* (2020); Pereira *et al.* (2024)

for AHSS starts from casting and progresses through rolling, annealing, forming, and joining stages, with each step carefully controlled to optimize microstructure and properties.

As shown in Table 3, different processing techniques are selected based on the target microstructure and component requirements, balancing performance with manufacturability.

Hot Forming Processes

Hot stamping, also known as press hardening, is one of the most important processes for producing ultra-high strength automotive parts. In this process, the steel blank is heated to the austenitizing temperature (typically above 900°C), formed in a press, and simultaneously quenched in the cooled dies. This results in a predominantly martensitic microstructure with tensile strengths exceeding 1500 MPa (Wróbel, 2022).

Hot forming significantly improves formability compared to cold stamping while reducing springback. The process allows the production of complex geometries that would be difficult or impossible with conventional cold forming of high-strength materials. Industrial adoption of hot stamping has grown rapidly due to its ability to produce lightweight, high-safety components such as B-pillars and door rings (Zhao *et al.*, 2018).

Laser Welding and Resistance Spot Welding

Welding and joining of AHSS require special attention due to the sensitivity of their microstructures to thermal cycles. Resistance spot welding (RSW) remains the dominant joining method in automotive assembly because of its speed and cost-effectiveness. However, AHSS welding can lead to issues such as softened heat-affected zones

and reduced joint strength, particularly in higher carbon grades (Manladan *et al.*, 2024).

Laser welding offers advantages in precision and reduced heat input, minimizing microstructural degradation. Advanced techniques, including in-process heat treatment and tailored welding parameters, help maintain the mechanical performance of welded AHSS joints. These joining technologies are essential for integrating AHSS into multi-material vehicle structures (Ighodaro, 2016).

Challenges in Machining and Forming

Despite their advantages, AHSS present several manufacturing challenges. High strength leads to increased tool wear, higher forming forces, and greater springback in cold forming operations. Edge cracking and limited hole expansion ratios are common issues in complex stampings. Hot stamping helps overcome some formability limitations but introduces challenges related to oxidation, coating systems, and distortion control (Frohn-Sørensen *et al.*, 2020; Pereira *et al.*, 2024).

Industrial manufacturability depends on careful process control, advanced lubrication, and die design. Steel producers continue to develop optimized chemistries and processing routes to improve weldability, coatability, and overall production efficiency. The integration of simulation tools for process design has become essential to reduce trial-and-error and accelerate implementation in automotive production lines.

APPLICATIONS OF AHSS IN THE AUTOMOTIVE INDUSTRY

Body-in-White Structures

AHSS grades such as Dual Phase (DP780), Martensitic (MS1500), and Press Hardened Steels (PHS1500–2000)

are widely used in body-in-white (BIW) components. Roof rails, pillars, and sills benefit from AHSS's high energy absorption and stiffness, ensuring passenger safety while reducing mass. For example, Docol® CR1700M roof rails improved crash performance and visibility while lowering costs compared to conventional steels (SSAB, 2025).

Crash Management Systems

Crash boxes, bumper beams, and side members employ AHSS grades like DP980 and TRIP steels, which exhibit superior work hardening and bake hardening effects. These properties enhance energy absorption and stabilize deformation during collisions, preventing premature splitting and ensuring predictable crash modes (AHSS Guidelines, 2025).

Chassis and Reinforcement Components

Chassis parts such as lower control arms, trailing arms, and subframes use Complex Phase (CP1000) and Hot-Rolled HR800HER steels. These grades deliver fatigue resistance, corrosion protection, and weight reduction. For instance, upgrading trailing arms from HR800CP to HR1000CP achieved a 13% weight reduction while improving durability (SSAB, 2025).

AHSS in Electric and Hybrid Vehicles

Electric vehicles (EVs) require strong yet lightweight structures to protect high-voltage batteries. AHSS solutions like Hex beam absorbers and coverless battery carrier frames provide superior crash protection and up to 37% mass savings in battery enclosures. These innovations

Table4. Automotive components and corresponding AHSS Application

A u t o m o t i v e Component	AHSS Grade Used	Purpose	Performance Benefit
Roof Rail	C R 1 7 0 0 M (Martensitic)	Structural stiffness, crash safety	Reduced weight, improved visibility
Car Sill Reinforcement	C R 1 4 0 0 M (Martensitic)	Side impact protection	Cost savings, high tensile strength
Front Bumper Beam	MS1500	Crash energy absorption	Enhanced crashworthiness
Crash Box	CP590	Controlled deformation	Stable crush mode, energy absorption
Lower Control Arm	H R 8 0 0 H E R , HR1000CP	Fatigue resistance	Weight reduction, corrosion resistance
Trailing Arm	HR1000CP	Axle alignment, durability	13% weight reduction, improved fatigue resistance
Battery Carrier Frame	PHS, CP steels	EV battery protection	37% mass savings, reduced CO ₂ emissions
B-Pillar	PHS1500	Passenger safety cage	High crash resistance, occupant protection

Sources: NIST, (2006); Baltazar-Hernández, (2023)

support sustainability goals by reducing lifecycle emissions and enabling safe autonomous EV architectures (Steel E-Motive, 2025).

Sustainability and Fuel Efficiency Benefits

AHSS enables 25% structural weight reduction, translating into 6–8% fuel economy improvement per 10% weight reduction (DOE, 2025). Compared to aluminum, AHSS offers 400 million metric tons of GHG savings by 2053, due to lower production emissions and near-100% recyclability (AISI, 2025).

CHALLENGES AND LIMITATIONS OF AHSS IN THE AUTOMOTIVE INDUSTRY

High Manufacturing Cost

AHSS production involves complex alloying and thermo-mechanical processing, which increases costs compared to conventional steels. Studies emphasize that while AHSS

reduces vehicle weight and improves crashworthiness, the higher cost of alloying elements and specialized heat treatments remains a barrier to widespread adoption (Hu & Feng, 2021). This cost challenge is particularly critical in mass-market vehicles where affordability is a priority.

Welding and Joining Difficulties

The multiphase microstructure of AHSS complicates welding. Resistance spot welding often leads to heat-affected zone (HAZ) softening, reducing joint strength. Research shows that AHSS welds exhibit lower fatigue resistance compared to base metals, limiting durability in crash-critical components (Baltazar-Hernández, 2023; NIST, 2006). Advanced techniques such as laser welding and friction stir welding are being explored, but they increase production complexity and cost.

Reduced Formability

Despite their strength, AHSS grades suffer from limited ductility and complex fracture behavior during forming. Conventional forming limit diagrams (FLDs) fail to predict fracture accurately in AHSS, leading to edge cracking and shear failures in automotive stamping operations (Pereira *et al.*, 2024). This reduced formability restricts design flexibility and requires advanced simulation models to optimize forming processes.

Springback Issues

Springback, the elastic recovery after forming, is more pronounced in AHSS due to their high yield strength. This leads to dimensional inaccuracies and assembly problems in body-in-white structures. Experimental studies on dual-phase steels show that springback prediction models often underestimate deformation, complicating industrial stamping operations (Mulidrán *et al.*, 2023). Solutions include optimized blank holding forces and

Table 4. Major challenges associated with AHSS

Challenge	Cause	Industrial Impact	Possible Solution
High Manufacturing Cost	Alloying elements, heat treatments	Limits affordability in mass-market vehicles	Optimize alloy design, scale production
Welding Difficulties	HAZ softening, microstructural sensitivity	Reduced joint strength, fatigue failures	Laser welding, friction stir welding, hybrid joining
Reduced Formability	Multiphase microstructure, fracture behavior	Edge cracking, limited design flexibility	Advanced fracture models, improved simulations
Springback Issues	High yield strength, elastic recovery	Dimensional inaccuracies, assembly errors	Optimized blank holding force, advanced hardening rules
Recycling Concerns	Mixed alloys, coatings	Higher recycling costs, energy use	Improved separation technologies, eco-friendly coatings

Sources: De Moor *et al.* (2018); Song *et al.* (2019)

advanced hardening models, but these add complexity to manufacturing.

Recycling and Sustainability Concerns

Although steel is highly recyclable, AHSS recycling faces challenges due to mixed alloy compositions and coatings. Lightweighting strategies improve fuel efficiency, but recycling AHSS requires specialized separation processes, increasing costs and energy use (Czerwinski, 2021). Compared to aluminum, AHSS offers lower production emissions, but sustainability concerns persist regarding end-of-life processing efficiency.

Critical Trade-Offs

The industrial limitations of AHSS highlight a performance–manufacturability trade-off. While AHSS enables lightweight, safe, and fuel-efficient vehicles, its manufacturing complexity, joining challenges, and recycling inefficiencies hinder large-scale adoption. Addressing these issues requires multi-material strategies, combining AHSS with aluminum or composites, and advancing predictive modeling for forming and joining.

FUTURE TRENDS AND RESEARCH OPPORTUNITIES

The evolution of Advanced High-Strength Steels (AHSS) is

closely tied to the demands of next-generation vehicles, particularly electric and autonomous platforms. Innovation in alloy design, processing, and sustainability is shaping the future of automotive materials.

THIRD-GENERATION AHSS DEVELOPMENTS

Third-generation AHSS (Gen3) combines the high strength of martensitic steels with improved ductility from transformation-induced plasticity (TRIP) and twinning-induced plasticity (TWIP) mechanisms. These steels aim to overcome the formability limitations of earlier generations while maintaining crash performance. Recent studies highlight Gen3 AHSS as a promising solution for complex automotive geometries without sacrificing safety (De Moor *et al.*, 2018).

AI-Assisted Alloy Design

Artificial intelligence (AI) and machine learning are increasingly applied to alloy design. By analyzing vast datasets of microstructural parameters, AI enables predictive modeling of mechanical properties, accelerating the discovery of optimized AHSS compositions (Xiong *et al.*, 2020). This approach reduces trial-and-error experimentation and supports cost-effective development of steels tailored for automotive needs.

NANO-ENGINEERED STEELS

Nano-engineering introduces ultrafine grain structures and nano-precipitates to enhance strength and toughness simultaneously. Research demonstrates that nano-structured AHSS can achieve superior fatigue resistance and crash energy absorption, making them ideal for battery enclosures and safety-critical EV components (Song *et al.*, 2019).

SUSTAINABLE AND RECYCLABLE STEEL SYSTEMS

Sustainability remains a priority, with emphasis on closed-loop recycling systems and eco-friendly coatings. Advances in metallurgical processing aim to reduce CO₂ emissions during steelmaking while ensuring recyclability of AHSS grades. Studies suggest that integrating green hydrogen-based steel production could drastically lower lifecycle emissions (Wang *et al.*, 2021).

INTEGRATION WITH ELECTRIC VEHICLE MANUFACTURING

Electric vehicles (EVs) demand lightweight yet protective materials for battery safety. AHSS is being engineered for battery carrier frames, crash absorbers, and underbody shields, balancing weight reduction with crashworthiness. Future research focuses on multi-material integration, combining AHSS with aluminum and composites to optimize EV structures (Li *et al.*, 2022).

CONCLUSION

Advanced High-Strength Steels (AHSS) have proven essential in balancing lightweighting and safety in modern automotive design. Their applications in body-in-white structures, crash management systems, chassis reinforcements, and electric vehicle battery protection demonstrate their versatility and impact. Despite challenges such as high manufacturing costs, welding difficulties, reduced formability, and recycling concerns, AHSS continues to evolve. Third-generation AHSS, AI-assisted alloy design, and nano-engineered steels represent promising pathways to overcome current limitations. Moreover, sustainable steelmaking and integration with EV manufacturing align AHSS with future automotive demands.

Authors' Contributions

The authors of this research have significantly contributed to the study's conception, data collection, and manuscript development. All authors were involved in writing the manuscript or critically reviewing it for its intellectual value. They have reviewed and approved the final version for submission and publication and accept full responsibility for the content and integrity of the work.

Acknowledgement

We thank all the researchers who contributed to the success of this research work.

Conflict of Interest

The authors declared that there are no conflicts of interest.

Funding

No funding was received for this research work

REFERENCES

1. AHSS Guidelines. (2025). Crash Management.
2. American Iron and Steel Institute. (2025). Steel sustainability in the auto market.
3. ArcelorMittal Global Automotive & Mobility Solutions. (2021). How AHSS is improving high voltage battery design.
4. Czerwinski, F. (2021). Current trends in automotive lightweighting strategies and materials. *Materials*, 14(21), 6631. <https://doi.org/10.3390/ma14216631>
5. De Moor, E. (2021). Advanced high-strength sheet steels for automotive applications. Colorado School of Mines.
6. De Moor, E., Speer, J. G., Matlock, D. K., & Merwin, M. J. (2018). Development of third-generation advanced high-strength steels for automotive applications. *Metallurgical and Materials Transactions A*, 49(3), 1074–1089.
7. Frohn-Sörensen, P., et al. (2020). Flexible manufacturing chain with integrated incremental sheet forming and subsequent joining. *Journal of Materials Processing Technology*.
8. H. (2023). Welding and joining of advanced high-strength steels. *Metals*, MDPI.
9. Hu, X., & Feng, Z. (2021). Advanced high-strength steel—Basics and applications in the automotive industry. Oak Ridge National Laboratory.
10. Huang, C., et al. (2022). Medium-Mn steels: From material design to failure mechanisms. *Materials Futures*. <https://doi.org/10.1088/2752-5724/ac7fae>
11. Ighodaro, O. (2016). Effects of metallic coatings on resistance spot weldability of advanced high strength steels [Doctoral dissertation]. University of Waterloo.
12. Ivković, D., et al. (2023). Review of the advanced high-strength steels used in automotive industry. *Mobility and Vehicle Mechanics*.

13. Jonsson, S. (2025). Evaluation of crashworthiness and fracture toughness at high deformation rates for advanced high strength steel sheets [Doctoral thesis]. DiVA Portal.
14. Kantanen, P., et al. (2022). Microstructures and mechanical properties of three medium-Mn steels processed via quenching and partitioning. *Materials Science and Engineering: A*, 831, Article 142123.
15. Kuziak, R., Kawalla, R., & Waengler, S. (2008). Advanced high strength steels for automotive industry. *Archives of Civil and Mechanical Engineering*, 8(2), 103–117.
16. Li, H., Chen, S., & Zhang, Y. (2022). Multi-material lightweight design strategies for electric vehicle structures. *Journal of Materials Engineering and Performance*, 31(5), 3456–3468.
17. Manladan, S. M., et al. (2024). Challenges and advances in resistance spot welding of advanced high-strength steels. *Journal of Materials Research and Technology*.
18. Matlock, D. K. (2009). Third generation of AHSS: Microstructure design concepts. *Proceedings of the International Conference on Advanced High Strength Sheet Steels*.
19. Mohapatra, S., et al. (2026). Impact behavior of automotive grade medium manganese steel: Reviews on current progress and challenges. *Materials at High Temperatures*. <https://doi.org/10.1177/02670836251412337>
20. Mulidrán, P., Spišák, E., Tomáš, M., Majerníková, J., Bidulská, J., & Bidulský, R. (2023). Impact of blank holding force and friction on springback prediction of dual-phase steel. *Materials*, 16(2), 811. <https://doi.org/10.3390/ma16020811>
21. NIST. (2006). Challenges and opportunities in joining advanced high-strength steels. U.S. Department of Energy.
22. Number Analytics. (2025). AHSS: The Future of Automotive Manufacturing.
23. Pereira, R., Peixinho, N., & Costa, S. L. (2024). A review of sheet metal forming evaluation of advanced high-strength steels. *Metals*, 14(4), 394. <https://doi.org/10.3390/met14040394>
24. Perka, A. K., et al. (2022). Advanced high-strength steels for automotive applications. *Metals*, 12(6), 1051.
25. Schmitt, J. H., et al. (2018). New developments of advanced high-strength steels for automotive applications. *Comptes Rendus Physique*, 19(8), 641–656. <https://doi.org/10.1016/j.crhy.2018.11.004>
26. Song, R., Ponge, D., Raabe, D., & Sun, J. (2019). Nano-structured steels for automotive safety applications. *Acta Materialia*, 165, 561–574.
27. SSAB. (2025). Chassis automotive components in AHSS steel.
28. SSAB. (2025). Structural automotive body components in AHSS steel.
29. Steel E-Motive. (2025). Electric vehicles Archives – AHSS Guidelines.
30. Wang, L., Zhang, Q., & Liu, Z. (2021). Hydrogen-based steelmaking for sustainable automotive materials. *Journal of Cleaner Production*, 278, 123–134.
31. WorldAutoSteel. (2025). AHSS Guidelines PR_FINAL.
32. Wróbel, I., et al. (2022). A review on hot stamping of advanced high-strength steels: Technological-metallurgical aspects and numerical simulation. *Symmetry*, 14(5), 969. <https://doi.org/10.3390/sym14050969>
33. Xia, et al. (2025). Review of performance of advanced high strength steels under impact. *Advanced Engineering Materials*. <https://doi.org/10.1002/adem.202402016>
34. Xiong, W., Olson, G. B., & Campbell, C. E. (2020). Machine learning in alloy design: Application to advanced high-strength steels. *npj Computational Materials*, 6(1), 1–10.
35. Zhao, J., et al. (2018). Thermomechanical processing of advanced high strength steels. *Progress in Materials Science*, 94, 174–242. <https://doi.org/10.1016/j.pmatsci.2018.01.002>

Cite this article: Moses Adondua Abah et.al. *A Critical Review of the Mechanical Properties and Applications of Advanced High-Strength Steels in the Automotive Industry International Journal of Research in Management Science and Engineering (IJRMSE) 2026; 3(1): 18-27.*

Copyright: © 2026. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.